

Tectyl RP 350

Oily Film, Water Displacing, Short-Term indoor Protection
MIL-C-16173 D GRADE 3, P-3 TYPE, KSM2212 KP-3



| INTRODUCTION |

Tectyl RP 350 is solvent cut-back rust preventive, has the property of dewatering and coat the ferrous or non-ferrous metal surface with an economical, soft oily type, and rust protecting film.

Tectyl RP 350 is easily removed by not only solvent cleaners but also alkali cleaners.

| PHYSICAL PROPERTIES |

Appearance	Dark Blown	Naked Eyes
Specific gravity (15/4°C)	0.81	ASTM D 1298
Flash Point (°C)	45	ASTM D 56
Kinetic viscosity (cSt, 40°C)	1.5	ASTM D 445
Oil Stain (82°CX24hrs)	Pass	MIL-C-22235A

- All data given in this Product Data Sheet are typical of this Product. It does not however constitute a specification. And, We reserve the right to modify products without prior notice

| PROTECTION PERIOD |

Condition	Period(mon)	e.g.
Mild	3 ~ 6	Relative humidity below 60%
Normal	1 ~ 3	Non-ventilated warehouse, Plant
Severe	Not	Exposed outdoor storage

- Above rust protection period may differ depending on working environment, surface condition, storage method and climate etc

| FEATURES |

- Soft Film, Resistant to moisture, salt, and acid vapor.
- Thin transparent oily film.
- Giving continuous rust protection.
- Easily removed by solvent or alkali cleaners.

| APPLICATION |

- Protection of parts which require water displacement.
- Protection of casting and forming parts.
- Protection of sintering alloys.
- Protection of steel wire, zinc galvanized wire and etc.

| HOW TO USE |

- Dip, Spray, Brush. (Recommended Temp, 10~35°C)
- Clean parts before applying.
- Do not dip when parts are hot.
- When Spray, keep low pressure.
- Use tank designed to drain and remove water regularly.
- Ventilate an area and be careful about fire on site.
- Minimize evaporation of solvent from tank.

| PACKING & SAFETY |

- Tank/Lorry, Tote, Drum(200LT), Pail(20LT)
- For your Safety, Refer to the Material Safety Data Sheet,