



Spheerol™ SBX 2

Heavy Duty Grease

Description

Castrol Spheerol™ SBX 2 Grease (previously called SBX Grease 2) is a smooth black lithium complex grease of a No. 2 consistency containing molybdenum disulphide and graphite solids.

Spheerol SBX 2 Grease is a unique blend of extreme pressure additives, solid lubricants and an effective corrosion inhibitor in a heavy viscosity synthetically modified base oil. It has a drop point (min) of 250°C and has a load carrying capacity exceeding 800kg under 4-Ball weld load tests.

Application

Originally designed to meet SKF requirements for sugar mill roller bearing grease. The extreme load capability of the grease makes it ideal for bucket pins, plain bearings and other heavy duty applications in the mining, sugar milling and general industrial industry.

The 5% molybdenum disulphide in Spheerol SBX 2 Grease meets certain minimum requirements of OEM's such as Caterpillar and Komatsu.

Advantages

- Solid lubricants – molybdenum disulphide 5%. helps maintaining separating film between gear tooth surfaces leading to minimising of gear tooth wear.
- Advanced EP additives provides excellent load carrying ability leads to protection from extreme loading
- Good water resistant properties helps in reducing grease consumption
- Good pumpability at low temperature ensures adequate grease supply during cold periods. Helps in avoiding equipment failure due to grease starvation.

Typical Characteristics

Name	Method	Units	Spheerol SBX 2
Appearance	Visual	-	Smooth black grease
Thickner Type	-	-	Lithium Complex
Consistency	ASTM D217 / ISO 2137	NLGI Grade	2
Base oil viscosity @ 40°C	ASTM D445	mm ² /s	1000
Timken OK Load	ASTM D2509	kg	20.4
Worked Penetration (60 strokes @ 25°C)	ASTM D217	1/10 mm	265-295
Four Ball Weld Load test, Kg	ASTM D2596	kg	800
Four Ball Wear test - Wear Scar Diameter (40 kgf / 75°C / 1200 rpm / 1 hr)	ASTM D2266	mm	0.52
Dropping Point	ASTM D2265	°C	250

Subject to usual manufacturing tolerances.

Additional Information

In order to minimise potential incompatibilities when converting to a new grease, all previous lubricant should be removed as much as possible prior to operation. During initial operation, relubrication intervals should be monitored closely to ensure all previous lubricant is purged.

Spheerol™ SBX 2

21 Dec 2016

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, to the extent that it is permissible by law to exclude warranties and representations, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. Refer to the MSDS, available from our website for further information. No responsibility is taken by either Castrol Australia, BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Australia Pty Limited - ABN 87 008 459 407 – 717 Bourke Street, Docklands Vic 3008
Technical Advice Line: 1300 557 998 Customer Service: 1300 722 088
<http://msdspd.castrol.com>