

# AMBERLITE™ MB20 Resin

Mixed Bed Resin for High Purity Water Applications

Description AMBERLITE<sup>™</sup> MB20 Resin is an ionically equilibrated mixed bed resin. It is a fully regenerated, ready-to-use mixture of a strong acid cation exchanger with a strong base type 1 anion exchanger. AMBERLITE MB20 Resin has been developed for the production of high purity water. It can be used for all applications requiring totally demineralised water, free of silica and of carbon dioxide.

The operating capacity of the mixed bed can be estimated using the following formula, which gives an approximate determination of volume of water that can be treated:



where BV (Bed Volume) is the number of litres of a feed water containing a TDS (Total Dissolved Solids) given in meq/L (or gals per  $ft^3$  resin with TDS as CaCO<sub>3</sub>) that can be demineralised with one litre of the resin mixture when run to exhaustion.

If required, AMBERLITE MB20 Resin can be regenerated after exhaustion. Both components must be separated by backwashing and regenerated separately.

Physical form	Mixture of white to amber spherical beads
Matrix	Styrene divinylbenzene copolymer
Functional groups	Sulphonic acid and trimethylammonium
lonic form as shipped	H*/OH⁻
Composition in volume	38-44% cation, 56-62% anion
Shipping density	715 g/L (45 lbs/ft <sup>3</sup> )
Particle size	
< 0.300 mm, max.	3%

## Suggested Operating Conditions

Typical Physical and Chemical Properties

Maxim	num operating temperature	60°C / 140°F
Minim	um bed depth	700 mm (2.3 ft)
Servic	e flow rate	20–40 BV*/h (2.5–5 gpm/ft <sup>3</sup> )
Reger	neration	
Туре		Cation: HCl or H <sub>2</sub> SO <sub>4</sub> ; Anion: NaOH

\*1 BV (Bed Volume) = 1 m<sup>3</sup> solution per m<sup>3</sup> resin or 7.5 gals per ft<sup>3</sup> resin

Packaging

25 liter bags or 7 cubic foot drum

### **Figure 1. Pressure Drop Data**

## Hydraulic Characteristics

#### Temperature = 20° C (68° F) gpm/ft2 0 8 12 16 20 24 28 32 36 40 2 8 7 1.5 Pressure Drop 6 5 bar/m Æ psi 4 3 0.5 2 1 0 0 20 10 30 50 60 70 80 90 100 0 40 m/h Linear Flow Rate

### For other temperatures use:

 $P_T = P_{20^{\circ}C} / (0.026 T_{\circ C} + 0.48)$ , where P = bar/m  $P_T = P_{68^{\circ}F} / (0.014 T_{\circ F} + 0.05)$ , where P = psi/ft

## Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## **Customer Notice**

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

DOW™ Ion Exchange Resins For more information about DOW™ resins, call the Dow Water & Process Solutions business:

North America:	1-800-447-4369	
Latin America:	(+55) 1 <mark>1-5</mark> 188-9222	
Europe:	(+32) 3-450-2240	
Pacific:	+60 3 7958 3392	
Japan:	+813 5460 2100	
China:	+86 21 2301 1000	
http://www.dowwaterandprocess.com		

Warning: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

