

INOPLAST AL

Self Adhesive Aluminium Butyl Membrane Waterproofing


Description

Inoplast AL is a single-faced adhesive tape of aluminum foil laminated polyester(PET) film substrate which is coated by excellent waterproof butyl rubber pressure-sensitive adhesive (PSA). This tape shows well-balanced adhesiveness in a wide range of temperature, and both substrate and PSA are excellent in air-tightness.

1. Structure



Application of Inoplast AL



2. Application

- Temporary fixing of exterior wall material, and waterproof packing of joints

3. Features

- Great weatherability
- Stable performance under variety of climate due to using special butyl rubber adhesive
- Superior water resistance
- Suitable for outdoor use and places where get contact with water. Since PET fabric backing can be coated with paint or mortar, the tape is good for use for outdoor waterproofing construction.
- Superior adhesive property
- Thick adhesive layer conforms well to rough surfaces, and helps obtaining long term waterproofing property when used for jointing of construction materials.
- Good adhesion to hard-to-adhere materials such as rubbers, foams, or polyethylene
- Excel in safety
- Can be used at places with limited ventilation due to containing no solvents. No worry for toxicity or fire disaster.

4. Adhesive properties

Test item		Unit	Value
Adhesion	BA SUS	N/10mm	8.97
	Concrete		13.20
Ball tack		Ball No.	37
Tensile strength		N/10mm	125
Elongation		%	15.6

【Test method】

Adhesion: In accordance with JIS Z 0237(2009)

Values in () are referential values from Inoplast Method

Ball tack: In accordance with Inoplast Method

Tensile and elongation: In accordance with JIS Z 0238(2009)

※All the values are examples of measured values, and not of guaranteed values.
 ※Specifications are subject to change without prior notice.

Test item		Unit	Value
Adhesion	Stainless	N/10mm	13.6
	Aluminum		13.4
	Steel		13.9
	Glass		13.6
	Slate (Top)		13.5
	Slate (Bottom)		13.4
	Bakelite		13.8
	PVC		13.6
	Polyethylene		13.3
	EPDM butyl rubber sheet		13.0
	Veneer		15.4
Tensile strength		N/10mm	125
Elongation		%	15.6

Measuring conditions : Temp.23°C Humidity 65%RH

Test methods :

Tensile strength : In accordance with JIS Z 1524 Article 7・9 (Interval: 125mm Peeling speed 300mm/min)


Elongation : % of elongation at break

Adhesion : JIS Z 1528 Article 6・7 (180°peeling)

Applying conditions : One reciprocation by metallic roller (2kg load, diameter 83mm, width45mm), which is covered by rubber (hardness 80HS, 6mm thick) at the speed of 300mm/min.

Peeling conditions: Peeling by 180°peel at the speed of 300mm/min after 20mins or more from application. Peeling resistance force to be adhesion.

5. Temperature dependency of adhesion



図－1 粘着力の温度依存性

Test plate : Stainless plate

Test method : Application of specimen at conditions of 23°C and 65%RH. Keep the specimen at each temperature for 20mins. Specimen to be peeled off at each temperature by 180°peeling.

6. Variation per time (Cycle test)




図-2 サイクル試験結果

Test plate : Stainless plate

Test method : Tape to be applied at 23°C, 65%RH.

Condition 1 : Thermostatic chamber at 80°C

Condition 2 : Water tank at 20°C

Specimen to be placed in condition 1 and 2 everyday (Cycle). After certain elapsed days, specimen to be kept under the circumstance of 23°C, 65%RH for 2hrs. Then adhesion to be measured by 180°peeling.

Remarks: No change in appearance (such as cracking, etc.) in this test

Adhesion of Inoplast AL increases as times elapse. Furthermore, no decline of adhesion even under water or rapid change of temperature.

7. Heat resistance property

表-3 耐熱性試験結果

項目	経日数 温度 °C		1	5	10	15
外観変化	50		亀裂 熱フロー (ダレ) } なし			
	75					
	100					
	120					

Test method : Specimen to be applied to glass plate vertically. Visual observation of appearance of specimen, which is placed in each temperature condition inside thermostatic chamber (50, 75, 100°C, and 120°C) after certain days. Inspection items: Adhesive flow, generation of crack, and shrinkage of tape

8. Cold resistance property

表-4 耐寒性試験結果

被着体	測定温度	-30°C	-40°C	-54°C	-60°C	-70°C
100 μ mポリエチレンフィルム		A	B	C	D	D
ケント紙		A	B	C	C	C

Judgment criterion

A : Nothing peculiar

B : Slight declination of flexibility, but no peel off

C : No flexibility and break off of tape, but no peel off

D : No flexibility and break off of tape, and tape peel off

Test method : In accordance with Fed. Method Std. №101B Method 2051

Specimen to be applied to polyethylene film or Kent paper at normal temperature. Keep

it under 65°C for 24hrs. Then keep it under each low temperature for 2hrs or more. Then roll it on iron bar which was also chilled under the same condition as specimen. Observe specimen's appearance. (Operation was also done in the same cooling condition) Inoplast AL performs its adhesion good enough under low temperatures.

9. Weather resistance

表-5 耐 候 性 試 験 結 果

項 目	単 位	照射時間	0 (常態)	100	300	500	1000
外 観	—	—	—	変化なし	変化なし	変化なし	変化なし
引 張 強 さ	kgf/25mm	—	7	7	7	7	7
伸 び	%	—	20	20	22	21	22
粘 着 力(ステンレス板)	gf/25mm	—	3,400	6,200	6,800	7,900	6,900

Test method : Weather-O-Meter conditions: 18mins of rain in 120mins cycle

25mm width specimen to be applied to stainless plate at room temperature. Appearance, tensile strength, and elongation of specimen were measured after exposed to sunshine carbon weather-o-meter (WE・SUN-HC) .

No declination of adhesion of Inoplast AL even after long term outside use. Furthermore, its adhesion even tends to increase in such condition. Moreover, no cracking, nor shrinking were found.

10. Standard dimensions and packing unit

Dimensions		
Width		Length
5 cm	×	1m
5 cm	×	20 m
10 cm	×	20 m
1 m	×	20 m

Please consult us when you have special requirement of different sizes.

※Quantity packed in a case is subject to change without prior notice.

11. Precautions for use

- (1) Please apply tape after removing dirt, dust, moisture and oil from the surface since enough adhesion is not obtainable if the surface is stained.
- (2) Please press firmly after applying the tape to obtain enough adhesion.
- (3) For the keeping of tape, please avoid direct sun-ray and the heat sources as heating equipment and store it at cool place.
- (4) Please do not use for electrical insulation purpose other than electrical insulation tape.
- (5) Please do not apply directly to the car body, furniture, walls, glass and PVC products since causing of discolor, adhesive residue, and paint peel-off.
- (6) Since adhesive residue and rash may be caused by using of other tapes than adhesive tape for skin, please do not apply the tape to the skin directly.
- (7) Please test well before actual use as tape may contaminate or leave adhesive depending on type of adherend.
- (8) Please consult us for special application.
(Toll free: 0 1 2 0 - 1 4 7 - 2 2 4)
- (9) Described values are examples of measured values, and not guaranteed values.
- (1 0) The lead-time varies by conditions. Please inquire us for obtaining updated information.
- (1 1) Specification may be subject to change without prior notice.
- (1 2) Please verify whether the tape is suitable for your application before

use.

- (1 3) We cannot be held responsible for any damage incurred as a results of using. Please use after enough confirmation.



PT. INORI INDONESIA
Niaga Kalimas 2 Blok C15-16, Bekasi
E-Mail : inori.office@inoriindonesia.com
Phone : +62 21 8269 1988