

PITT-CHAR® XP

DESCRIPTION

Solvent-free, thick-film intumescent epoxy coating, for hydrocarbon pool and jet fires

PRINCIPAL CHARACTERISTICS

- Highly durable intumescent coating for protection of steel against hydrocarbon and jet fires; typical applications include: Offshore – structural steel members, bulkheads and decks; Onshore – pipework, storage tanks and vessels
- Unique flexibility offers enhanced performance on vibrating structures and in conditions of explosion overpressure
- Suitable for use in cryogenic conditions
- Good resistance to splash and spillage of chemicals
- Excellent abrasion resistance
- Suitable for corrosivity categories up to C5-I and C5-M
- Meets the requirements for Norsok M501 rev 5 accelerated aging tests
- Approved by ABS, BV, DNV, LR, UL and GASAFE

COLOR AND GLOSS LEVEL

- Gray
- Matt

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.06 kg/l (66.2 lb/ft ³)
Volume solids	100%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 0.0 g/kg max. 0.0 g/l (approx. 0.0 lb/US gal)
Recommended dry film thickness	1000 - 7000 µm (40.0 - 280.0 mils) per coat
Theoretical spreading rate	1.06 kg/m ² for 1000 µm (0.22 lb/ft ² for 40.0 mils)
Dry to touch	10 hours
Overcoating Interval	Minimum: 4 hours Maximum: 1 month
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- The applied density is dependent upon many variables such as temperature, test method and application method
- The required dry film thickness must be in accordance with the approval certification
- See ADDITIONAL DATA – Curing time
- See ADDITIONAL DATA – Spreading rate and film thickness

PITT-CHAR® XP

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Approved primer must be sound, dry and free from any contamination
- Where mesh reinforcement of PITT-CHAR® XP is necessary, this should be carried out in accordance with the PITT-CHAR® XP APPLICATION GUIDELINES

Substrate temperature and application conditions

- Ambient temperature below 10°C (50°F) is acceptable; however curing to hardness takes longer, and it will cease curing below 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- Relative humidity during application and curing should not exceed 85%

INSTRUCTIONS FOR USE

Mixing ratio

- By volume: base to hardener 2.33 : 1
- By weight: base to hardener 3.05 : 1

Note: For details see PITT-CHAR XP Application Guidelines

Pot life

45 minutes at 25°C (77°F)

Airless spray

Recommended thinner

THINNER 60-30

Volume of thinner

5 - 7%, but the quantity shall never exceed 10%

Nozzle angle

40° for large flat surfaces

Nozzle orifice

Approx. 0.69 – 0.89 mm (0.027 – 0.035 in)

Nozzle pressure

35.0 MPa (approx. 350 bar; 5077 p.s.i.)

Notes:

- The addition of thinner will affect sag resistance and overcoating intervals
- Material (mixed) temperature needs to be between 23°C (73°F) and 35°C (95°F)
- The maximum length of the hoses should not exceed 30 m (98.4 ft)
- Use of spray equipment with a ratio of 74:1 is recommended

PITT-CHAR® XP

Airless spray: Plural component

Recommended thinner

No thinner should be added

Nozzle angle

40° for large flat surfaces

Nozzle orifice

Approx. 0.84 – 1.09 mm (0.033 – 0.043 in)

Nozzle pressure

24.0 - 31.0 MPa (approx. 240 - 310 bar; 3481 - 4496 p.s.i.)

Notes:

- Nozzle angle 40° (for large flat surfaces)
- Twin feed spray equipment utilizing a minimum 10 inch king air motor is recommended
- Base and hardener need to be pre-heated to a minimum of 55 - 60°C (131 - 140°F) while circulating through the unit
- Suitable insulated and/or heated hoses should be used

Trowel

Recommended thinner

THINNER 60-30

Volume of thinner

0 - 2%

Note: Recommended for small areas and touch-up only

Cleaning solvent

THINNER 90-53

PITT-CHAR® XP

ADDITIONAL DATA

Curing time for solvent-free application				
Substrate temperature	Dry to walk on	Time to outdoor exposure	Dry to handle	Full cure
5°C (41°F)	30 hours	70 hours	3.5 days	1.5 months
10°C (50°F)	26 hours	45 hours	52 hours	1 month
20°C (68°F)	18 hours	18 hours	18 hours	15 days
30°C (86°F)	10 hours	7 hours	10 hours	10 days
40°C (104°F)	4 hours	5 hours	7 hours	7 days

Notes:

- Curing times may vary depending on substrate, ambient and material temperature
- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG’s specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer’s discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer’s failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG’s knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user’s responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer’s responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.