

MasterEmaco[®] P 5000 AP

Single component, cement based, multi-use, bonding and active protective primer

DESCRIPTION

MasterEmaco P 5000 AP active primer, not only reinstates a high pH environment it also contains active corrosion inhibiting additives for the protection of reinforcement steel. It can also be used as an adhesive bonding slurry for subsequent repair mortars.

MasterEmaco P 5000 AP is a ready-to-use material that contains Portland cement, well graded fine fillers, re-dispersible powder and special additives.

When mixed with water, it forms a slurry that can be applied by brush to the clean exposed reinforcement, or directly on the dampened, prepared concrete substrate when used as a bonding coat.

FIELDS OF APPLICATION

MasterEmaco P 5000 AP is used for the protection of reinforcement steel:

- When steel is visible and the available depth of cover is less than 10 mm
- When concrete is contaminated with chlorides
- In critical environments when extra protection is specified
- When the timing at the jobsite does not allow for the repair mortars to be applied immediately after cleaning the steel

MasterEmaco P 5000 AP can also be used to aid bond and application properties of hand applied repair mortars in extreme thicknesses and conditions.

BENEFITS

- Meets all major national and international norms for steel priming in concrete repair systems
- Excellent rust inhibiting properties as it reinstates a high pH environment.
- Contains active corrosion inhibitors to further protect the steel
- Polymer modified for additional adhesive bond to the steel

- Does not affect the pull out strength of reinforcement steel
- Perfect compatibility with steel rebars and concrete or repair mortars
- Simply mixed with water

Multi-use: can also be used as a bonding slurry to improve bond and application

- thicknesses of **MasterEmaco** repair mortars on prepared concrete surfaces
- Light grey/off white color for easy site control of reinforcement coverage
- Supplied in re-usable air-tight containers
- • Low chromate (Cr[VI] < 2 ppm)

PACKAGING

MasterEmaco P5000 AP is available in 5kg units.

MasterEmaco® P 5000 AP

Single component, cement based, multi-use, bonding and active protective primer

TECHNICAL DATA

Property	Standard	Unit	Values
Appearance	-	-	Light Grey Powder
Layer Thickness	-	-	2 mm in two layers
Density		g/cm ³	Approx. 1.8
Mixing water		l/kg	Approx. 0.22 – 0.26
Working time		minutes	Approx. 60 minutes (cold climate) Approx. 20 minutes (hot climate)
Temperature for application(support & material)		°C	Between +5 and +35
Pull out strength of coated rebar	Comparison vs. uncoated	%	> 80
ZTV-Sib90 Compliance testing	TL BE-PCC	Weight %	< 0.05
• total halogen content		µA/cm ²	< 10
• corrosion stimulation		mm	< 1 (migration of rust underneath the coating starting from uncoated edge)
• corrosion resistance			
• accelerated weathering			
10 cycles DIN 50017			
10 cycles DIN 50018			
120 hours DIN 50021			No corrosion/No delamination/ Max. crack width < 0.1 mm

Hardening times are measured at 21°C + 2°C and 60% + 10% relative humidity. Higher temperatures will reduce these times and lower temperatures will extend them. Technical data shown are statistical results and do not correspond to guaranteed minima. Tolerances are those described in appropriate performance standards.

APPLICATION GUIDELINES

SURFACE PREPARATION: STEEL REINFORCEMENT

All corrosion and its by-products must be removed. The preparation should meet the requirements of ISO 8501-1 / ISO 12944-4 class SA 2 for the full 360° circumference of the steel reinforcement to be coated.

SURFACE PREPARATION: CONCRETE

When used as a bond coat on concrete, the surface must be completely clean and structurally sound. Remove deteriorated or contaminated concrete or mortar, e.g. by grit or high pressure water blasting. Saturate the concrete surface with water but remove excess before application.

MIXING:

In a suitable container, mix **MasterEmaco P 5000 AP** with a paddle mounted on a slow-speed drill, or by hand, until a smooth, thick consistency is achieved. Use only clean, uncontaminated water.

MIXING WATER NEEDED:

0.22 to 0.26 liters per kg of powder, depending upon consistency required. Leave to stand for approx. 5 minutes and re-mix briefly before use, adjusting the consistency when required, without exceeding the maximum water demand.

APPLICATION OF SLURRY:

Substrate temperatures must be a minimum of +5°C and a maximum of +35°C. The minimum temperatures must be maintained during application and for at least 24 hours thereafter for optimum curing of the product.

AS A REINFORCEMENT PRIMER:

Apply the mixed material in an even layer at least 1mm thick (approx. 1.5kg/m²) to the full circumference of the prepared reinforcement using a soft paint brush. When the first coat has hardened sufficiently, (approx. 30-90minutes) apply a second coat also 1mm thick. It is important that this second layer has sufficiently

MasterEmaco® P 5000 AP

Single component, cement based, multi-use, bonding and active protective primer

hardened before the repair mortar is applied. When applying the repair mortar by hand this can be done after approximately 2 hours. However, when spraying a repair mortar the priming coat must be left to dry completely (min. 8 hours @ 20°C).

As a bonding slurry: Work the mixed material well into the prepared and pre-soaked, damp surface by using a brush. Typical application rates are 2-3kg per m². Apply the repair mortar wet in wet. Never allow the slurry bond coat to dry out!

CLEANING OF TOOLS

While still wet clean with water. Once dry/cured the material can only be removed mechanically.

CURING

Curing times are dependent on the environmental conditions. Protect from rainfall until finally set.

COVERAGE

Approx. 1.5 kg of dry powder per m² and 1 mm layer thickness.

This consumption is theoretical and depends on the roughness of the substrate. It should be verified on each particular job by means of "in situ" tests.

STORAGE

Store in cool and dry warehouse conditions. Shelf life in these conditions is 12 months in unopened original sacks.

WATCH POINTS

- Do not apply at temperatures below +5°C nor above +35°C
- Do not add cement, sand or other substances that could affect the properties of the material
- Never add water or fresh mortar to a mortar mix

which has already begun to set

- Contact Technical Department of your local BASF Construction Chemicals office regarding any information required not mentioned here

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when manipulating this product, for example do not eat, smoke or drink while working and wash your hands when taking a break or when the job is completed. Specific safety information in the handling and transport of this product can be found in the Material Safety Data Sheet.

Avoid contact with eyes and prolonged contact with skin. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Call a physician. In case of contact with skin, wash skin thoroughly. The disposal of the product and its container should be carried out according to local legislation in force. Responsibility for this lies with the final owner of the product.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

CONTACT

Should you require any further information, please do not hesitate to contact us:

Web: www.master-builders-solutions.sa

E: enquirycc.saudi@basf.com

M: +966 13 853 8600

Saudi BASF for Building Materials Co., Ltd.

P.O. Box 1884, Al Khobar, KSA

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with BASF and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.