

Epoxy acrylate (styrene-free) resin based high performance anchoring grout

DESCRIPTION

MasterFlow 920 ANS is a two-component epoxy acrylate resin based high performance anchoring grout for use in cracked and uncracked concrete under normal as well as seismic conditions (seismic category C1). It is a styrene-free system with very low voc content. MasterFlow 920 ANS has extended gel and cure time for tropical temperatures.

USES & APPLICATIONS

- Structural applications in cracked and un cracked concrete applications in seismic zones (C1)
- Reinforcing & starter bars
- Suspended ventilation systems
- Safety barriers
- Machinery & heavy machinery
- Racking
- Rolling cranes

APPROVALS & TESTS

- ETA according ETAG 001 Part 1 and Part 5 Option 1 for anchoring of threaded bars into cracked and uncracked concrete application in seismic zones (C1)
- ETA according to TR023 for post-installed rebar connections
- Tested according to LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)
- A+ as per French VOC Regulation
- WRAS Suitable for use with potable water













European Technical Assessment ETA 15/0600. BASF Construction Solutions GmbH. 1020. MasterFlow 920 ANS. DoP MF920ANSTR029. ETAG 001-Part 1 and Part 5 Option 1 used as an EAD, For fixing and/or supporting to concrete, structural elements (which contributes to the stability of the works) or heavy units.

European Technical Assessment ETA 15/0601. BASF Construction Solutions GmbH. 15. 1020. MasterFlow 920 ANS. DoP MF920ANSTR023. ETAG 001-Part 1 Technical Assessment ETA and Part 5 used as an EAD. For fixing and/or supporting concrete structural elements or heavy units such as cladding and suspended ceilings.

FEATURES

- Anchors may be placed close to free edges
- Suitable for dry, wet & flooded holes
- Reduced drilling diameters i.e. M20 only requires a 22mm hole and M24 requires only a 26mm hole making it an economical injection system
- Variable embedment depths
- Ratio of 10:1

PACKAGING

MasterFlow 920 ANS is available in boxes of 12 co-axial cartridges of 380ml and boxes of 12 single piston foil pack cartridges of 300ml

INSTALLATION PROCEDURE

Please refer to the method statement or contact BASF Technical Services department.





WORKING & LOADING TIMES

Resin cartridge Temperature	T Work	Base Material Temperature	T Load		
+15 to +20°C	15 mins	+15 to +20°C	5 hours		
+20 to +25°C	10 mins	+20 to +25°C	145 minutes		
+25 to +30°C	7.5 mins	+25 to +30°C	85 minutes		
+30 to +35°C	5 mins	+30 to +35°C	50 minutes		
+35 to +40°C	3.5 mins	+35 to +40°C	40 minutes		

T Work is typical gel time at highest base material temperature in the range. T Load is set at the lowest base material temperature in the range

PHYSICAL PROPERTIES

Property		Value	Test Standard
Compressive Strength	24 hours	72.3N/mm²	A CTM DC05 @ 120°C
Compressive Strength	7 days	77.8N/mm²	ASTM D695 @ +20°C
Compressive Madulus Strongth	24 hours	5GN/m²	ACTM DCOF @ +20°C
Compressive Modulus Strength	7 days	7GN/m²	ASTM D695 @ +20°C
Tanaila Ctranath	24 hours	13.5N/mm²	ACTM DC20 @ +20°C
Tensile Strength	7 days	15.2N/mm²	ASTM D638 @ +20°C
Tensile Strength Elongation at	24 hours	6%	ACTM DC20 @ +20°C
Break	7 days	6.7%	ASTM D638 @ +20°C
Tensile Modulus	24 hours	3.75GN/m²	ACTM D629 @ +20°C
Terislie Modulus	7 days	3.8GN/m²	ASTM D638 @ +20°C
Flexural Strength	24 hours	29.3N/mm²	A STM D700 @ 120°C
Fiexulai Sueligui	7 days	38.7N/mm²	ASTM D790 @ +20°C

THEORETICAL NUMBER OF FIXINGS PER CARTRIDGE

Applies to installations in solid substrates only


Cartridge Volume	h _{ef}	Ø8	Ø10	Ø12	Ø16	Ø20	Ø25	Ø32
		Drilling Ø 12mm	Drilling Ø 14mm	Drilling Ø 16mm	Drilling Ø 20mm	Drilling Ø 25mm	Drilling Ø 32mm	Drilling Ø 40mm
	10d	49	32	22	13	6	3	1
300ml	12d	41	27	19	10	5	2	1
	20d	24	16	11	6	3	1	0
	10d	63	42	29	16	8	3	2
380ml	12d	53	35	24	14	7	3	1
	20d	31	21	14	8	4	1	1

Note: Jobsite/contractor installations usually result in more resin being injected than the theoretical requirement resulting in lower number of fixings per cartridge. The reduction to the number of fixings per cartridge in practice is greater for smaller diameter holes and shallower embedment depths.





INSTALLATION PARAMETERS



MasterFlow 920 ANS with REINFORCING BARS (ANCHOR THEORY)

Diameter of rebar (mm)	10	12	16	20	25	32
Drilled hole diameter (mm)	14	16	20	25	32	40

DESIGN RESISTANCE

Rebar siz	е			Ø10	Ø12	Ø16	Ø20	Ø25	Ø32		
Effective	embedment	depth h _{ef}	[mm]	90	110	125	170	250	300		
non-cracked concrete temperature range (-40°C / +40°C)											
tension	C20/25	$N_{Rd,p}$	[kN]	18.85	23.04	34.91	53.41	98.17	92.15		
shear	C20/25	$N_{\text{Rd,s}}$	[kN]	9.33	14.67	20.67	57.33	90.00	147.33		

RECOMMENDED RESISTANCE

Rebar siz	е			Ø10	Ø12	Ø16	Ø20	Ø25	Ø32		
Effective	embedment	depth h _{ef}	[mm]	90	110	125	170	250	300		
	non-cracked concrete temperature range (-40°C / +40°C)										
tension	C20/25	$N_{Rd,p}$	[kN]	13.46	16.46	24.93	38.15	70.12	65.82		
shear	C20/25	N _{Rd,s}	[kN]	6.67	10.48	14.76	40.95	64.29	105.24		

 f_{yk} = 500 N/mm²

Partial safety factor γ 1.4


For resistance values in higher temperatures, please contact BASF Technical Services.

All the above resistance values are considering combined pull out and concrete cone failure in tension and steel failure in shear.





MasterFlow 920 ANS with REINFORCING BARS (REBAR THEORY)



INSTALLATION PARAMETERS Diameter of rebar 8 10 12 16 20 25 32 Drilled hole diameter 12 14 16 20 25 32 40

DESIGN RESISTANCE

Rebar size				Ø8	Ø10	Ø12	Ø16	Ø20	Ø25	Ø32
Effective	embedment	[mm]	110	140	170	230	280	350	680	
cracked concrete (static cracks) temperature range (-40°C / +40°C)										
tension	C20/25	N _{Rec,p}	[kN]	9.4	14.7	21.2	37.5	58.6	91.6	224.9

RECOMMENDED RESISTANCE

Rebar siz	е		Ø8	Ø10	Ø12	Ø16	Ø20	Ø25	Ø32	
Effective	embedment	[mm]	110	140	170	230	280	350	680	
cracked concrete (static cracks) temperature range (-40°C / +40°C)										
tension	C20/25	$N_{Rd,p}$	[kN]	6.6	10.3	14.8	26.2	41.0	64.1	160.64

 f_{yk} = 500 N/mm²

For resistance values in higher temperatures, please contact BASF Technical Services.

All the above tension loads are valid for good bond conditions according to EN 1991-1-1. For all other conditions multiply the value by 0.7

All the above resistance values are considering combined pull out and concrete cone failure in tension and steel failure in s





STORAGE & SHELF LIFE

Cartridges should be stored in their original packaging, the correct way up, in cool conditions (+5°C to +25°C) out of direct sunlight.

When stored correctly, the product shelf life will be 12 months from the date of manufacture.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.

 $\ensuremath{ \mathbb{R}}$ = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/FI_920ANS_10_15/v5/02_18/v6/05_18/v7/09_18

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.







^{*} Properties listed are based on laboratory controlled tests.