

# MasterSeal® M 640

Flexible and elastic single component polyurethane waterproofing membrane

## DESCRIPTION

**MasterSeal M 640** Membrane is a single component, polyurethane based, elastomeric coating for roof waterproofing

## RECOMMENDED USES

**MasterSeal M 640 Membrane** is recommended for:

- Applicable for both inside and outside use
- Can be employed on concrete and cement mortar.
- Waterproofing of roofs, balconies and terraces.

Contact your local BASF Construction Chemicals office regarding any application required not mentioned here

## FEATURES AND BENEFITS

- **High elasticity and flexibility** – moves with structure.
- **Excellent adhesion to concrete and mortar** - Fully bonded system.
- **Impermeable to water and carbon dioxide** - protects from corrosion of the steel.
- **Easy to apply.** Single component and low viscosity.
- **Excellent crack bridging capacity** - even at low temperatures.
- **Monolithic** – no laps, welds or seams.
- **Fast Application** - Can be re-coated after only a few hours

## PERFORMANCE DATA

Shore A hardness : (ASTM D 2240)	Approx. 65±5
Crack bridging (EOTA TR 008)	>2mm
Elongation at break : (DIN 52455)	Approx. 600%
Tensile strength : (DIN 52455)	> 4 MPa
Adhesion to concrete: (ASTM D 903)	> 2 N/mm <sup>2</sup>
Water vapour permeability : (ISO 9932: 91)	Approx. 25 g/m <sup>2</sup> /day

Solar Reflectance (SR) (ASTM E 903-96)	0.87
Solar Emittance (ASTM E 408 -71)	0.89
Application temperature (support and material)	From +5 to +35 °C
Open to pedestrian traffic	Approx. 12 hours
Fully cured :	After 7 days

## PROPERTIES

Density	1.32 g/cm <sup>3</sup>
Solid Content	83%
Working Time @ 20°C	40 minutes
Re-coating interval @ 20°C	Min. 12 hours
	Max. 48 hours
Rain Safe @ 20°C	4 Days
Service temperature :	From -20 to +80 °C

Higher temperatures and/or higher R.H. can shorten these times, and vice versa.

## APPLICATION

### Application method

**(a) Surface Preparation:** All substrates (new and old) must be structurally sound, dry and free of laitance and loose particles.

Clean of oil, grease, rubber skid marks, paint stains and other adhesion impairing contaminants.

Profile mechanically the surface by shot blasting, high pressure water jetting or other suitable mechanical preparation method.

After surface preparation the tensile strength of the substrate should exceed 0.7 N/mm<sup>2</sup> (check with an approved pull-off tester).

Temperature of the substrate should be minimum +5°C and maximum +35°C. The residual moisture content of the substrate must not exceed 4% (check with e.g. CM device). The temperature of the substrate must be at least 3°C above the current dew point temperature. Try to keep the temperatures uniform during application and hardening

# MasterSeal<sup>®</sup> M 640

**(b) Primer:** Suitable primer for using **MasterSeal M 640** on concrete or cementitious mortar substrates is **MasterSeal P 2525** or **MasterEmaco P 2525**. Refer to PDS for application guidelines.

**(c) Mixing:** **MasterSeal M 640** is a single component product. Does not require mixing. Homogenize with mechanical stirring before use.

**(d) Application:** **MasterSeal M 640** is applied in two coats using a brush, a short hair roller or an air-less spray gun. After mixing pour the contents of **MasterSeal M 640** on to the primed substrate and spread with a roller or brush at a minimum consumption of 0.7 Kg/m<sup>2</sup> per layer. After a gap of minimum 12 hours and maximum 36 hours apply second layer of the **MasterSeal M 640** Membrane. If needed, apply a third layer of the **MasterSeal M 640** Membrane.

**(e) Reinforcement:** In joints or any singular points like wall floor connections, chimneys, pipes, etc. reinforce **MasterSeal M 640** with a mat installed on the still wet material. Press it to soak, and saturate again with enough **MasterSeal M 640**.

**(f) Top Coat:** **MasterSeal M 640** does not have sufficient UV and Weather resistance to be used in exposed applications without protection. In exposed conditions apply one or two coats of **MasterSeal TC 640**. Refer to PDS for application guidelines. **MasterSeal TC 640** can be broadcasted with dry silica sand to provide a hard wearing, slip resistant finish.

## For best performance:

- The product must not be applied when the temperature is below +10°C or above 30°C.
- Do not mix solvents, sand or other products that could affect the products properties must not be added.
- Do not apply in more than 0.6mm thickness per layer.
- It is recommended to use a reinforcement mat. If an application without this mat is required, apply three coats of products.

## ESTIMATING DATA

**Consumption:** Normally Approx. 1.5 to 2.5 kg/m<sup>2</sup> are required in two coats depending on chosen application method. These consumptions are theoretical and can vary according to the application conditions. It is essential to carry out representative trials on site to evaluate the exact consumption.

## PACKAGING

**MasterSeal M 640** is available in 25kg pails.

**Colour:** White, Grey and Red.

## SHELF LIFE

**MasterSeal M 640** has a shelf life of 9 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

## PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

® = registered trademark of BASF group in many countries

MAP#MasterSeal M 640 v1-0916

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

### BASF Construction Chemicals Asia Pacific

33 Tuas Avenue 11  
Singapore 639090

Tel: +65 68616766

Website: [www.master-builders-solutions.asiapacific.basf.com](http://www.master-builders-solutions.asiapacific.basf.com)