

Report of Analysis

CODE SAMPLE : BRIKET BATUBARA 02/09/2021
DATE OF RECEIVED : September 6, 2021
DATE OF ANALYSIS : September 6, 2021
QUANTITY : 1 Bag

Pengujian ini dilakukan oleh Laboratorium Penguji Batubara PTBA Peltar.

NO.	PARAMETER	RESULT	
		% ADB	% AR
1	Total Moisture (TM)		24.37
2	Proximate Analysis		
	- Inherent Moisture	13.49	-
	- Ash Content	6.97	6.09
	- Volatile Matter	40.69	35.57
	- Fixed Carbon	38.85	33.96
3	Total Sulphur	0.65	0.57
4	Calorific Value (CV)		
	- Gross CV, Kcal/Kg	5686	4971

Catatan : Hasil pengujian ini hanya berlaku untuk 1 bag sampel

September 7, 2021
 PT BUKIT ASAM Tbk.
 UNIT PELABUHAN TARAHAN



Hairul Saleh
AM. Laboratorium

PT Bukit Asam Tbk.

Tanjung Enim
 Sumatera Selatan, Indonesia
 Telephone (+62 711) 311104, 310005
 (+62 734) 451202, 451206
 Facsimile (+62 734) 451095, 451099

Jakarta
 Menara Kadin Indonesia Lt. 9 & 15
 Jl. HR Rasuna Said Blok X-5 Kav. 2-3
 Jakarta 12950, Indonesia
 Telephone (+62 21) 5254014
 Facsimile (+62 21) 5254002

Ombilin
 Sawahlunto
 Sumatera Barat, Indonesia
 Telephone (+62 754) 61021
 Facsimile (+62 754) 61402

Padang
 Jl. Tanjung Peruk No. 1
 Teluk Bayur Sumatera Barat,
 Indonesia
 Telephone (+62 751) 62522;
 63522; 31996
 Facsimile (+62 751) 63533

Tanjungkarang
 Jl. Soekarno Hatta KM. 15, Tarahan
 Bandar Lampung, Indonesia
 Telephone (+62 721) 31545; 31686
 Facsimile (+62 721) 31577

Kertapati
 Jl. Stasiun Kereta Api, Palembang
 Sumatera Selatan, Indonesia
 Telephone (+62 711) 512617
 Facsimile (+62 711) 511388