

Conplast WP400

Hydrophobic pore-blocking waterproofing admixture

Uses

Conplast WP400 will drastically reduce water absorption in structural and precast concrete. It is suitable for use in below ground structures, reinforced concrete in marine areas, piles, water retaining structures, manholes, waste water treatment and desalination plants.

Advantages

- Bitumen ammonia free system
- Provides integral protection, ensuring reduced absorption throughout the concrete
- Integral protection is maintained even if surface damage occurs, unlike applied surface films or coatings
- Lower water:cement ratio improves compressive strength at same workability
- Fully compatible with certain Fosroc surface coatings and finishes

Description

Conplast WP400 chloride free admixture is supplied as a turbid liquid which instantly disperses in water.

Conplast WP400 is an organic liquid which reacts with products of the cement hydration process to produce a hydrophobic material which repels external water, reducing absorption into the concrete.

Technical support

Fosroc provides a technical advisory service for on-site assistance and advice on admixture selection, evaluation trials and dispensing equipment. Technical data and guidance can be provided for admixtures and other products for use with fresh and hardened concrete.

Dosage

The optimum dosage of Conplast WP400 to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. This allows the optimization of admixture dosage and mix design and provides a complete assessment of the mix. The normal recommended dosage is 1.5 to 2.0 litres per 100 kg of cement.

Effects of overdosing

An overdose of double the intended dose of Conplast WP400 may result in increased retardation and workability, hence reduce the short term strength development. Long term strength is unlikely to be affected. But depend on the mix design, certain mix design may slightly reduce compressive strength.

Use at other dosages

Dosages other than those given on this sheet may be used to meet particular mix requirements provided that adequate supervision is available. Compliance with requirements must be assessed through trial mixes. Contact the Fosroc Technical Department for advice in these cases.

Properties

Appearance	: Turbid solution
Specific gravity	: Typically 1.02 – 1.05 at 25°C
Chloride content	: Nil (Not intentionally Added)

Instructions for use

Compatibility

Conplast WP400 is compatible with most of Super plasticizer when used in the same concrete mix, but should be added to the mix separately and must not be mixed together prior to addition. The resultant properties of mixes containing more than one admixture should be assessed by the trial mix procedure recommended on this data sheet.

Conplast WP400 is suitable for use with all types of Portland cements, SRC cements and cement replacement materials such as PFA, GGBFS and microsilica.

Dispensing

The correct quantity of Conplast WP400 should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results. Contact the Fosroc Technical Department for advice regarding suitable equipment and its installation.

Curing

As with all structural concrete, good curing practice should be maintained, particularly in situations where an overdose has occurred. Water spray, wet hessian or a Concure** spray applied curing membrane should be used.



Conplast WP400*

Typical performance example

Many variables in concreting materials and conditions can affect the selection and use of an admixture. Trials should be carried out using relevant materials and conditions in order to determine the optimum mix design and admixture dosage to meet specific requirements.

A typical performance example from evaluation studies of Conplast WP400 is included on this data sheet. The values quoted are representative of results obtained and are provided as illustrations of the performance.

Laboratory testing with mix design using Cement Content 350 kg/m³, W/C = 0.4,

Conplast WP400 = 1%

Slump (before added Conplast WP) = 18 cm

Slump (after added Conplast WP) = 18 cm

Absorption (BSI1881 part 122) = 0.5%

Note: as water reducer, we use Conplast SP337, SNF based Superplasticizer.

Limitations

The use of Conplast WP400 will not make poor quality concrete waterproof. Good concrete practice must be followed at all times. Well graded aggregates must be used and a minimum cement content of 300 kg/m³ is recommended (exclude cement replacement). Highly recommended using W/C 0.4, maximum 0.45. To get that W/C, mix design must be combined with Superplasticizer as water reducer.

Fosroc recommend Superplasticizer series like:

- Conplast SP337
- Conplast SP430 , Or similar.

Separate TDS available on request.

Adequate water bars must be provided between lifts of concrete and floor bays.



PT. FOSROC Indonesia

Jl.Akasia II Blok A8 No.1
Delta Silicon Industrial Park
Lippo Cikarang
Bekasi 17550
Indonesia

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Estimating

Supply

Conplast WP400	:	210 liter drums
		and 1000L IBC tank

Storage

Conplast WP400 has a shelf life of 12 months if the temperature is kept within the range of 20°C to 35°C.

Precautions

Health and safety

Conplast WP400 is alkaline and should not be swallowed or allowed to come into contact with skin and eyes.

Wear suitable protective gloves and goggles. In case of contact with the skin, wash immediately with soap and water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting. For further information consult the Safety Data Sheet available for this product.

Fire

Conplast WP400 is water based and non-flammable.

Cleaning and disposal

Spillages of Conplast WP400 should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Hose down remnants with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.

* Denotes the trademark of Fosroc International Limited

† See separate data sheet