

PRODUCT DATA SHEET

SikaGrout[®]-215 (new)

HIGH PRECISION, GENERAL PURPOSE, NON-SHRINK CEMENTITIOUS GROUT

DESCRIPTION

A non-shrink, cementitious premixed grout with extended working time to suit local ambient temperatures.

USES

For grouting over a wide range of applications:

- Anchor bolts
- Machine bedding/base plates
- Supporting bridge bearing pads
- Pre-cast concrete section
- Dry pack applications
- Cavities, gaps and recesses
- For grouting method of concrete repair
- Marine structure

CHARACTERISTICS / ADVANTAGES

- Easy to use, just add water
- Good flow characteristic
- Adjustable consistency
- Rapid strength development
- Shrinkage compensated
- High final strength
- Non-Corrosive
- Non-Toxic

PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	Powder / Grey
Shelf life	6 months from the date production if stored in undamage and unopened original sealed bags
Storage conditions	Stored in dry condition between +10 °C - +30 °C
Density	~2.26 kg/L

TECHNICAL INFORMATION

Compressive Strength	1 day	~25.0 N/mm ²	(ASTM C-109)
	3 days	~40.0 N/mm ²	
	7 days	~52.0 N/mm ²	
	28 days	~65.0 N/mm ²	
Tensile Strength in Flexure	28 days	> 6.0 N/mm ²	(ASTM C-348)

Tensile Adhesion Strength	28 days	>1.5 N/mm ² Concrete failure, over roughened concrete surface
	28 days	>2.5 N/mm ² Over mechanically roughened old grout surface
Expansion	1 - 3 h (at +27 °C)	0.30 - 1.40 % (ASTM C-940)

APPLICATION INFORMATION

Mixing Ratio	4.0 L per 25 kg bag (water per powder = 16 % by weight)		
Consumption	~1 940 kg/m ³ of mortar		
Yield	~12.80 L per 25 kg bag		
Layer Thickness	Recommended thickness is 20 - 100 mm		
Flowability	Flow cone (mm)	240 - 280 mm	(ASTM C230/230M)
Product Temperature	< +30 °C		
Ambient Air Temperature	+10 °C - +35 °C		
Substrate Temperature	+10 °C - +35 °C		
Pot Life	25 min		
Setting Time	4 - 8 h		

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

SURFACE PREPARATION

- Remove dirt, oil, grease, loose material and other bond-inhibiting materials.
- Anchor bolts to be grouted must be degreased with suitable solvent.
- Concrete must be sound and roughened to promote mechanical adhesion.
- Prior to pouring, surface must be wetted to saturated surface dry.

FORMING

For pourable grout, construct forms to retain grout without leakage. Forms should be lined or coated with bond-breaker for easy removal. Forms should be sufficiently high to accommodate head of grout. Where grout tight form is difficult to achieve, use SikaSet Accelerator as water plug (refer to PDS SikaSet Accelerator).

MIXING

Put measured quantity of water (depend on the required consistency) into a mixing vessel. Add slowly the total contents of SikaGrout®-215 (new) while mixing. Mix continuously for 3 minutes to achieve even consistency. Use a mechanically low speed drill (400 - 600 rpm) with mixing paddle or appropriately sized mortar mixer.

APPLICATION

Within 25 minutes after mixing, place grout into forms from one side to avoid air entrapment. Do not vibrate. Use a suitable head box of 150-200 mm and maintain the grout head at all times to ensure a continuous flow. Gentle tapping or pulling loops of wire from one side may assist the flow of the mortar under difficult working conditions.

CURING TREATMENT

Wet cure for a minimum 3 days with wet hessian, plastic sheet or apply a curing compound (Antisol)

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened and / or cured material can only be remove mechanically.

IMPORTANT CONSIDERATIONS

- Minimum application thickness : 10 mm
- Recommended thickness of SikaGrout®-215 (new) in one pour is 20 mm to 100mm.
- If the thickness exceeds 100 mm, special procedure must be taken to anticipate temperature rise. Iced water, add coarse aggregate to the mix (max. 40% by powder weight), or both of them may be used to eliminate temperature rise.
- Variations in cement could cause shade differences in colour of the mortar.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia Head Office and Manufacturing

Jl. Raya Cibinong-Bekasi Km.20
Limusunggal-Cileungsi
Bogor 16820-Indonesia
Tel. +62 21 8230025, Fax +62 21
8230026



Product Data Sheet
SikaGrout®-215 (new)
June 2020, Version 05.01
020201010010000128

SikaGrout-215new-en-ID-(06-2020)-5-1.pdf