

MasterSeal M800

A highly elastic, non-solvented, ultra fast curing, spray applied polyurethane coating for use in waterproofing applications

DESCRIPTION

MasterSeal M800 is a non-solvented, two component waterproofing membrane. It is highly reactive and can only be applied by special two component spray equipment.

FIELD OF APPLICATION

MasterSeal M800 is used in a variety of waterproofing applications including roofing, balconies, podium and car park decks, cut and cover tunnelling and basement waterproofing.

MasterSeal M800 can be applied to the majority of substrates irrespective of falls. Spray delivered and ultra-fast cure enables easy application to form a monolithic waterproofing membrane on simple and complex surfaces.

MasterSeal M800 yellows in ultraviolet light unless coated with an appropriate UV resistant topcoat.

Refer to individual system data sheets.

FEATURES AND BENEFITS

- Application to vertical surfaces without runs
- Easy application to complicated details
- Fast installation
- Can be applied to a wide range of substrates with the appropriate primer
- Monolithic – no welds or seams
- No welding, no torches, no hot works
- High water vapour permeability – low risk of blistering
- Excellent mechanical properties
- Excellent crack bridging properties
- Root resistant
- Resistant to standing water
- Thermoset – does not soften at high temperatures and remains elastic at low temperatures; Tg approx. -45°C
- Non-solvented
- Approved by the United Kingdom Water Regulations Advisory Scheme, listing No 0804514
- BBA Approved membrane

SUBSTRATE PRETREATMENT

The primer, or base layer to which MasterSeal M800 is to be applied must be clean and dry and free from oil, grease and loose material and any other contamination which might impair adhesion.

Primer selection will depend on substrate type. Application should take place within the recoat interval of the primer, or base layer, to which it is to be applied. Refer to product data sheet.

APPLICATION CONDITIONS

For best results substrate and air temperature should be in the range $5-40^{\circ}\text{C}$.

Spray machine equipment, e.g. Reaku type, will precondition the membrane components to the correct temperature prior to application. However, in very cold conditions the use of barrel heaters may be required to ensure the optimal operation of barrel pumps.

The temperatures should not fall below the minimum stated until the material is fully cured. The temperature of the substrate must be at least 3°C above the dew point both during the application and for at least a further 2 hours (at 15°C).

APPLICATION

MasterSeal M800 can only be applied by means of a suitable two component spray machine. The choice of machine depends on the type and size of work and the ease of access. For advice, please contact Master Builders Solutions UK Ltd

Due to the fast reaction it is possible to rapidly build thickness from 1.5 to $> 6\text{mm}$.

MasterSeal M800 is available with the Part A coloured white and the Part B coloured black. This results in a uniform grey colour of the sprayed material thus giving the sprayer a visual control of the quality of the mixing, and machine faults become immediately obvious. If the membrane colour changes, stop spraying and check machine settings etc.

Check mix ratios are correct at the start of spraying and regularly throughout the day.

Surrounding areas should be protected from overspray by masking off. Care should be taken to prevent spray mist being carried by wind by erecting suitable barriers.

COVERAGE

MasterSeal M800 is normally applied at $1.5-2.0\text{kg/m}^2$, this corresponds to a thickness of $1.5-2.0\text{mm}$. Details require a higher coverage rate up to 4.0kg/m^2 or more.

MasterSeal M800

A highly elastic, non-solvented, ultra fast curing, spray applied polyurethane coating for use in waterproofing applications

FINISHING AND CLEANING

Tools must be cleaned immediately after use with xylene or other suitable solvent.

CURING

Full cure is reached in 2 days after the application at a constant temperature of 20°C.

WORKING TIME

18 seconds when hand mixed at 23°C ambient and substrate temperature.

PACKAGING

MasterSeal M800 is supplied in drums.

<i>Component A</i>	<i>210 kg</i>
<i>Component B</i>	<i>220 kg</i>

STORAGE

Store in original containers under normal warehouse conditions. Off the ground, dry and at a temperature between 5–30°C. Do not expose to direct sunlight.

SHELF LIFE

For maximum shelf life under these conditions, see "Best before....." label.

EU Regulation 2004/42 (Decopaint Guideline)

This product conforms to the EU directive 2004/42/EG (Deco-Paint directive) and contains less than the maximum allowable VOC limit (Stage 2, 2010).

According to the EU directive 2004/42, the maximum allowable VOC content for the Product Category IIA / j is 500 g/l (Limit: Stage 2, 2010). The VOC content for MasterSeal M800 is < 500 g/l (for the ready to use product).

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed.

Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet. For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

CONTACT DETAILS

Master Builders Solutions UK Ltd
19 Broad Ground Road
Lakeside
Redditch
Worcestershire
B98 8YP

Tel: +44 (0) 1527 512255

Fax +44 (0) 1527 503576

www.master-builders-solutions.com/en-gb

© Master Builders Solutions UK Ltd

MasterSeal M800

A highly elastic, non-solvented, ultra fast curing, spray applied polyurethane coating for use in waterproofing applications

Product Data	
Mixing ratio	
By weight	100:73
By volume	100:70
Density g/cm ³ at 20°C	
Component A	1.05
Component B	1.10
Gel time / sec	
Hand mixed at 23°C	18
Recoat intervals at 20°C	
Minimum / hours	2
Maximum / hours	6
Fully cured at 20°C / d	2
Ambient and substrate temperature	
Minimum / °C	5
Maximum / °C	40
Relative humidity maximum / % RH	85
Physical properties after 28 days	
Shore A hardness	75
Tensile Strength DIN53504 / MPa	8
Elongation DIN53504 / %	400

The above figures are intended as a guide only and should not be used as a basis for specifications.



When MasterSeal M800 is used as a membrane with other MasterTop and MasterSeal products the system conforms to the relevant CE marks.

Please refer to the relevant Declaration of Performance and the product and system data sheets.

MasterSeal M800

A highly elastic, non-solvented, ultra fast curing, spray applied polyurethane coating for use in waterproofing applications

MasterSeal M800 - Master Builders Solutions UK Ltd, Version 1

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.