

Visi Carbon – Carbon Graphite Grade

GX-02 *New Improve*

Typical Properties

Bulk Density	g/cm ³	1,72
Grain Size	μm	15
Hardness	Shore	45
Specific Resistance	≤μΩm	12
Compressive Strength	≥MPa	60
Flexural Strength	≥MPa	32
Tensile Strength	≥MPa	18,0

All properties measured room temperatures except for C.T.E.

C.T.E. = Coefficient Thermal Expansion (R.T. to 1000°C)

Flexural Strength determined using third point loading

All properties are typical values and are not to be used for specification limits