

## Visi Carbon – Isostatic Graphite Grade

# GA-52

## Typical Properties

Bulk Density	g/cm <sup>3</sup>	1,83
Grain Size	μm	7
Hardness	Shore	62
Specific Resistance	≤μΩm	12,5
Compressive Strength	≥MPa	107,8
Flexural Strength	≥MPa	53,9
Tensile Strength	≥MPa	26,9

All properties measured room temperatures except for C.T.E.

C.T.E. = Coefficient Thermal Expansion (R.T. to 1000°C)

Flexural Strength determined using third point loading

All properties are typical values and are not to be used for specification limits