

LAPORAN HASIL UJI (LHU)

L e m b a r : **A S L I.**

N o m o r : 1872-E/BPPI/BRSBB/04/2016.

Tgl. Diterbitkan : 15 April 2016.

C o n t o h : Wood Pellet.

No.	Parameter Uji	Satuan	Hasil Uji	Metode Uji
			P. 1180 (1)	
1.	Diameter.	mm	8,20	Gravimetri
2.	Length.	mm	50,20	Gravimetri
3.	Unit Volume Massa.	-	0,76	Gravimetri
4.	Total Moisture.	%	5,01	Gravimetri
5.	Net Colorific Value.	Cal/ g	4292,24	Bomb Calorimetri
6.	Ash.	%	1,42	Gravimetri
7.	Chlorine.	%	0,07	Titrimetri
8.	Sulphur.	%	0,31	Gravimetri
9.	Nitrogen.	%	0,21	Titrimetri
10.	Ash Fusion Temperature.	%	82,54	Gravimetri
11.	Fines :			
	- Hg.	ppm	0,0128	A A S
	- Cd.	ppm	< 0,0020	A A S
12.	Minor Elements :			
	- Pb.	ppm	< 0,0090	A A S
	- As.	ppm	< 0,0003	A A S
	- Cr.	ppm	< 0,0020	A A S
	- Cu.	ppm	16,5981	A A S
	- Ni.	ppm	2,1556	A A S
	- Zn.	ppm	42,4652	A A S

Laboratorium Pengujian Komoditi dan Lingkungan

Manajer Teknis,

