

Certificate No. 05484/EOBOAK

Date: October 18, 2017



Issuing Office: Jl. Jend. A. Yani. No. 315 Surabaya 60234, Indonesia Phone/Facs: +62 31 8470547/8470563 Email: labsurabaya@sucofindo.co.id

REPORT OF ANALYSIS

CLIENT

CV. MAHKOTA CITRA MANDIRI

Jl. Pogot 27 RT. 002 RW. 005 Tanah Kali Kedinding, Kenjeran

Surabaya – Jawa Timur.

THE FOLLOWING SAMPLE (S) WAS/ WERE SUBMITTED AND IDENTIFIED BY CLIENT AS:

TYPE OF SAMPLE

CHARCHOAL

DATE OF RECEIVED

October 13, 2017

DATE OF ANALYSIS

October 14 up to 18, 2017

TEST REQUIRED

Full Analysis

DESCRIPTION OF SAMPLE

Form

Charchoal

Weight / Volume :

± 1 Kg.

Unsealed plastic bag.

Packing

SAMPLE IDENTIFICATION

(STATED BY CLIENT)

. . .

We have tested the sample (s) submitted and the following results were obtained:

Parameters	Unit	AR (As Received)	DB (Dry Basis)	Test Method
Total Moisture	% wt	3.7		ASTM D 2961 - 17
Ash Content	% wt	1.7	1.7	ASTM D 3174 - 12
Volatile Matter	% wt	35.2	36.5	ASTM D 3175 - 17
Fixed Carbon	% wt	59.4	61.8	ASTM D 3172 - 13
Total Sulfur	% wt	0.15	0.15	ASTM D 4239 - 14e2
Gross Calorific Value	Kcal/K	6783	7044	ASTM D 5865 - 13

This Certificate/report is issued under our General Terms and Conditions, copy of which is available upon request or may be accessed at www.sucofindo.co.id

Dept. of &

Coal and Minerals

BUCOFINDO

amanad Soleh

7103051701217



SCI-2007A

Certificate No. 05484/EOBOAK

Date: October 18, 2017



Issuing Office:
Jl. Jend. A. Yani. No. 315 Surabaya 60234, Indonesia
Phone/Facs: +62 31 8470547/8470563
Email: labsurabaya@sucofindo.co.id

REPORT OF ANALYSIS

CLIENT

: CV. MAHKOTA CITRA MANDIRI

Jl. Pogot 27 RT. 002 RW. 005 Tanah Kali Kedinding, Kenjeran

Surabaya - Jawa Timur.

THE FOLLOWING SAMPLE (S) WAS/ WERE SUBMITTED AND IDENTIFIED BY CLIENT AS:

TYPE OF SAMPLE

: CHARCHOAL

DATE OF RECEIVED

October 13, 2017

DATE OF ANALYSIS

October 14 up to 18, 2017

TEST REQUIRED

Full Analysis

DESCRIPTION OF SAMPLE

Form

Charchoal

Weight / Volume

± 1 Kg.

Packing

Unsealed plastic bag.

SAMPLE IDENTIFICATION

(STATED BY CLIENT)

We have tested the sample (s) submitted and the following results were obtained:

Parameters	Unit	AR (As Received)	DB (Dry Basis)	Test Method
Total Moisture	% wt	3.7	\\ \	ASTM D 2961 - 17
Ash Content	% wt	1.7	1.7	ASTM D 3174 - 12
Volatile Matter	% wt	35.2	36.5	ASTM D 3175 - 17
Fixed Carbon	% wt	59.4	61.8	ASTM D 3172 - 13
Total Sulfur	% wt	0.15	0.15	ASTM D 4239 - 14e2
Gross Calorific Value	Kcal/K	6783	7044	ASTM D 5865 - 13

This Certificate/report is issued under our General Terms and Conditions, copy of which is available upon request or may be accessed at www.sucofindo.co.id

Dept. of Commercial 3 - Coal and Minerals

Mobaminad Soleh

7103051701217

5607840

SC1-2007AC