

ProRox SL 970^{SA}
 Old Equivalent Grade: RockTech S650.128

High temperature slab



Applications

ProRox SL 970^{SA} is a strong and rigid stone wool slab, for the thermal and acoustic insulation of constructions where higher temperatures and light mechanical loads (e.g. vibrations) occur. Typical examples are ovens, furnaces and exhaust ducts.

Compliance

ProRox SL 970^{SA} Slabs comply with the requirements as set by internationally recognized standards like CINI 2.2.01 and ASTM C612 Type IA,II, III, IVA and IVB.

Advantages

- Suitable for high temperature application
- Retains shape
- Available in a wide range of thicknesses

Product properties

	Performance							Standard
	Mean Temp (°C)	50	100	150	200	250	300	
Thermal Conductivity	λ (W/mK)	0.038	0.043	0.049	0.056	0.064	0.074	ASTM C177
Nominal Density	128 kg/m ³							ASTM C303
Maximum Service Temperature	650°C							ASTM C411/ C447
Linear Shrinkage	Less than 2% (at max service temperature)							ASTM C356
Reaction to Fire	EuroClass A1 Surface burning characteristics; Flame spread = passed, Smoke development = passed							EN 13501-1 ASTM E84
Chloride Content	Less than 10 ppm Conforms to the stainless steel corrosion specification as per ASTM C795							ASTM C871 ASTM C692/ C871
Moisture Absorption	Less than 1% weight							ASTM C1104/ C1104M
Water Absorption	Less than 1 kg/m ²							EN 1609

Note: All information and data for technical parameters are based on laboratory testing.